

1. PRODUCT DESCRIPTION

A. COMPOSITION

Quik-Glaze FC is a state of the art, high solids, and UV stable, aliphatic elastomeric polyurea. It is a low VOC and low odor during application and cure. Quik-Glaze FC is a fast curing coating system which enables fast turnaround times. Quik-Glaze FC does not require the use of plural component spray apparatus. Quik-Glaze FC has been specially formulated to have a working time of 12 minutes with a hard dry in 2 hours at 70°F (21°C). It is available in a high gloss clear formulation. Contact CPC for recommendation for satin finishes.

When fully cured, Quik-Glaze FC will provide superior durability and is an optional top coat for most flooring systems such as Decor-Flor, Microtopping, Stamp-Cote, Tek-Crete, Elastatex 500, Colorflake, stained concrete and many more. Quik-Glaze FC's properties makes it one of the very best sealers for maintaining and preserving elaborate decorative finishes.

Quik-Glaze FC is extremely color stable and displays excellent UV weathering characteristics.

B. TYPICAL USES

Quik-Glaze FC adheres well to many substrates including cementitious polymer modified overlays, concrete, steel and resinous floors. The balance of fast turn around time, excellent abrasion resistance, flexibility and elongation is well suited for various harsh applications. Some typical floor applications include: Cold storage areas, food service preparation areas, beverage service areas, decorative entry foyers, high traffic areas, promenade decks and roof decks, labs, pharmaceutical production, and areas exposed to chemical use (see chemical resistance chart).

C. ADVANTAGES AND LIMITATIONS

ADVANTAGES:

1. Fast cure.
2. High tear strength.
3. Excellent abrasion resistance.
4. Excellent chemical resistance
5. Displays excellent UV resistance.
6. Longer pot life than conventional polyurea product.
7. High gloss finish.
8. Resistant to chemicals (Refer to Quik-Glaze FC Chemical Resistant Chart).
9. Installed only by Professional Factory Trained Dex-O-Tex Contractors.

LIMITATIONS:

1. Rapid cure means a corresponding short working time.
2. This coating displays excellent abrasion resistance and physical properties but can still incur damage from shape blades. Proper precautions should be taken to eliminate sharp objects from "slicing" the coating.
3. Polymer floor coatings, including those manufactured by Crossfield Products Corp., may show staining of tire marks from some brands and types of tires. Crossfield Products Corp. does not warrant its materials against tire staining.
4. Moisture vapor emission rates (MVER) in excess of 3.0 lbs./1000 sq. ft./per 24 hour period per ASTM F1869, or an

rh in excess of 78% per ASTM F2170 may result in delamination, discoloration or improper curing without proper treatment prior to installation of the flooring system. Consult with Crossfield Products Corp. for specific recommendations.

3. Vapor control primers, sloping, smoothing or leveling compounds, crack repair or isolation, waterproof membranes or other supplementary items may be required for proper installation at an additional cost. Consult with Crossfield Products Corp. for specific recommendations.

2. TYPICAL PHYSICAL PROPERTIES at 75°F (24°C)

- A. **Tear Strength** ASTM D624, Die C..... 879 psi
- B. **Flexibility** ASTM D1737**..... Passes 180 degree bend, 1/8" Mandrel
- C. **Tensile Strength** ASTM D412 4,700 psi
- D. **Tensile Elongation** ASTM D412 80%
- E. **Taber Abrasion** ASTM D4060 8 mg loss (CS17 Wheel, 1000g Load, 1000 Cycles)
- F. **Impact Resistance** ASTM D2794,
 - Direct.....160in/lbs
 - Reverse160in/lbs
- G. **Hardness** ASTM D2240 Shore D..... 80-85
- H. **Solid Percent by Weight** (calculated)..... 99.9%
- I. **Gloss** ASTM D523..... 88+
- J. **Dry Time** 50% relative humidity
 - Surface Dry.....1.5 hrs
 - Hard Dry2.0 hrs
- K. **Pot Life** 50% relative humidity..... 20 min
- L. **Coefficient of Friction** ASTM D2047.....0.67 dry (slip resistance with leather footwear).....0.82 wet
- M. **Microbial Resistant** ASTM G21..... Passes Rating 1
- N. **Chemical Resistance Test Procedures**

The tabulation of chemical damage is intended as a general guide only. Much more extensive tables of chemical resistance are available from Crossfield, including tests conducted on reagents at higher temperatures, etc. The Crossfield laboratories are available to conduct specialty testing on particular chemicals under simulated service conditions. (See Chemical Resistance Chart)

3. OVERVIEW OF INSTALLATION STEPS

- A. Prepare surfaces by removal of laitance, grease, foreign matter, etc. Prepare substrate in accordance with SSPC SP 13/NACE 06.
- B. Apply appropriate Primer.
- C. Apply Quik-Glaze FC in two or three coats as specified.

4. PRODUCT AVAILABILITY

Crossfield Products Corp. maintains offices and/or factories at all addresses listed below. Factory Trained Contractors are established in all major trading areas in the United States, Canada and various European, Latin American and Far East nations.

Product Description Sheet

5. SKID RESISTANCE and CLEANABILITY

In general the more aggressive the finished surface the greater the coefficient of friction and corresponding skid resistance, the more difficult to clean. The smoother the finished texture the easier the surface is to clean, but there is a loss of skid resistant properties.

6. CLEANING

Cleaning and disinfecting compounds and cleaning techniques can affect the color, gloss, texture and performance of the system. As a precautionary step, Crossfield recommends that the end-user test their cleaning and disinfecting compounds on a sample or on a small, out of the way finished area, utilizing the intended cleaning technique prior to cleaning the entire surface area. If no deleterious effects are observed, the procedure can be continued. If the cleaning and disinfecting compounds or cleaning techniques damage the system, modification of the cleaning material or techniques will be required. Contact your Representative for additional information.

7. SPECIFICATION ASSISTANCE

Consult Crossfield Products Corp. for specification assistance, detailing, etc. This consultation is highly recommended prior to specification.

8. TESTING

The technical data contained herein is the result of tests made in Crossfield's laboratories or in independent laboratories using small scale equipment, following generally accepted trade practices. Although this information is believed to be true and accurate, the use of different equipment for testing under dissimilar conditions or the testing of samples produced under dissimilar conditions may develop substantially different results.

LIMITED WARRANTY

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICE ARE MET.

Crossfield Products Corp. warrants to the purchaser of its products that such products are free from manufacturing defect. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield's obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and which Crossfield examination shall disclose to Crossfield's satisfaction to be thus defective.

IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION, ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIALS NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCT OR PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.



DEX-O-TEX PRODUCT LINE Crossfield Products Corp.

West Coast Office
3000 E. Harcourt Street
Rancho Dominguez, CA
90221
310-886-9100
310-886-9119 fax

East Coast Office
140 Valley Road
Roselle Park, NJ
07204
908-245-2800
908-245-0659 fax



www.dexotex.com