

DEX-O-TEX®

System Description Sheet

Terracolor

Troweled Epoxy Floor

3/16" to 1/4" Decorative Aggregate Floor with Integral Covebase

1. PRODUCT DESCRIPTION

A. COMPOSITION

Terracolor is a thin-section, trowel applied, decorative flooring system, designed to produce a seamless floor and cove base. Terracolor is installed at 3/16" (4.75mm) to 1/4" (6.33mm) thickness. Terracolor consists of pre-engineered decorative aggregates embedded in a colored epoxy matrix. It is finished with clear epoxy that offers superior scratch resistance and withstands heavy abuse and impact.

Terracolor may be applied over new and existing concrete, metal or wood substrates (consult Crossfield for detailed specifications).

It can be finished with optional topcoats of clear (gloss) or matte finish, Dex-O-Tex Posi-Tred CR when subjected to extreme environmental conditions or Quik-Glaze a highly chemical and abrasion resistant polyurea topcoat.

Terracolor is available in an Antimicrobial Additive incorporating an anti-microbial biocide, which protects against growth of algae, bacteria, fungi, mold, mildew, yeast, etc.

Terracolor is often used in conjunction with Dex-O-Tex Wall-Glas to produce an integrated "cocoon effect" seamless floor and wall system.

B. TYPICAL USES

Terracolor is designed to be used in facilities where aesthetics and functionality are both required, such as, pharmaceutical plants, research and development, bio-tech, clean rooms, medical facilities, laboratories, commercial kitchens, food processing, institutional facilities, food and beverage processing, wine and spirits and other facilities requiring an aesthetic functional floor.

C. ADVANTAGES AND LIMITATIONS

ADVANTAGES:

1. Monolithic, including base
2. Chemical resistant.
3. Decorative finish.
4. Easily maintained.
5. High compressive strength
6. Installed only by Professional Factory Trained Dex-O-Tex Contractors.

LIMITATIONS:

1. Discoloration may occur under UV exposure, use Dex-O-Tex Quik-Glaze where UV stability is required.
2. Cracking of substrate may reflect through flooring system (Crack isolation membrane will reduce this possibility).
3. May be incorporated with a Dex-O-Tex Waterproof or crack isolation membrane.
4. Moisture vapor emission rates (MVER) in excess of 3.0 lbs/1000 sq./ft./per 24 hr. period per ASTM F1869, or an rh in excess of 78% per ASTM F2170 may result in delamination, discoloration or improper curing without proper treatment prior to installation of the flooring system. Consult with Crossfield Products Corp. for specific recommendations.

5. Vapor control primers, sloping, smoothing or leveling compounds, crack repair or isolation, waterproof membranes or other supplementary items may be required for proper installation at an additional cost. Consult with Crossfield Products Corp. for specific recommendations.

2. TYPICAL PHYSICAL PROPERTIES at 75°F (24°C)

- | | |
|--|---|
| A. Compressive Strength ASTM C579 | 10,000 psi
(Resin, Hardener & Aggregate) 703 kg/cm |
| B. Compressive Strength ASTM D695 | 11,000 psi
(Resin and Hardener) 774 kg/cm |
| C. Tensile Strength ASTM C307 | 1,400 psi
(Resin, Hardener & Aggregate) 98 kg/cm |
| D. Tensile Strength ASTM D638..... | 5,000 psi
(Resin and Hardener) 352 kg/cm |
| E. Flexural Strength ASTM C580..... | 4,000 psi
281 kg/cm |
| F. Surface Hardness ASTM D2240, Shore D | 80-85 |
| G. Adhesion ASTM D4541..... | > 400 psi
(100% concrete failure) |
| H. Flammability ASTM D635..... | Self-extinguishing by
this test (0.6") |
| I. Flammability ASTM E648, FTMS 372, PA 253, NBSIR
75-950Critical Radian Heat Flux | > 1.03 Watts/cm ² |
| J. Smoke Density ASTM E662 D _s (1.5) ≤ 0.00, D _s (4.0) ≤ 0.89 | |
| K. Abrasion Resistance ASTM D4060..... | 0.04 gr
(CS17, 1000gr load, Cycles) |
| L. Indentation Characteristics MIL-D-3134..... | >1.0% |
| M. Impact Resistance Gardner Impact Test (160 lbs.) | No cracking or detachment |
| N. Microbial Resistance ASTM G21 | Passes Rating 1 |
| O. Chemical Resistance (See Chemical Resistance Chart) | |

3. OVERVIEW OF INSTALLATION STEPS

- A. Surface Preparation:** Surface shall be clean, dry and sound free from laitance, dirt, grease, oil, bond inhibiting compounds, curing agents or other foreign matter.
- B. Primer:** Apply by brush, roller or trowel.
- C. Basecoat:** Trowel apply Terracolor mix to a nominal thickness of 3/16" (4.75mm) to 1/4" (6.33mm). Compact matrix material into a tight, smooth even finish.
- D. Sealer:** Apply multiple seal coats to provide a smooth, even impervious finish. If skid resistance is required, provide desired surface texture by roller or by incorporating a slip resistant aggregate.

4. PRODUCT AVAILABILITY

Crossfield Products Corp. maintains offices and/or factories at all addresses listed below. Factory Trained Contractors are

System Description Sheet

Terracolor Troweled Epoxy Floor 3/16" to 1/4" Decorative Aggregate Floor with Integral Covebase

established in all major trading areas in the United States, Canada and various European, Latin American and Far East nations.

5. SKID RESISTANCE and CLEANABILITY

In general, the more aggressive the finished surface the greater the coefficient of friction and corresponding skid resistance, the more difficult to clean. The smoother the finished texture the easier the surface is to clean, but there is a loss of skid resistant properties.

6. CLEANING

Cleaning and disinfecting compounds and cleaning techniques can affect the color, gloss, texture and performance of the system. As a precautionary step, Crossfield recommends that the end-user test their cleaning and disinfecting compounds on a sample or on a small, out of the way finished area, utilizing the intended cleaning technique prior to cleaning the entire surface area. If no deleterious effects are observed, the procedure can be continued. If the cleaning and disinfecting compounds or cleaning techniques damage the system, modification of the cleaning material or techniques will be required. Contact your Representative for additional information.

7. SPECIFICATION ASSISTANCE

Consult Crossfield Products Corp. for specification assistance, detailing, etc. This consultation is highly recommended prior to specification.

8. CHEMICAL RESISTANCE

See Crossfield Products Corp.'s. Chemical Resistance Guidelines for chemical resistance of a product or system, as well as the types of test performed:

- ASTM C868 Standard Test Method for Chemical Resistance of Protective Lining.
- ASTM C267 Standard Test Method for Chemical Resistance of Mortars, Grouts, and Monolithic Surfacing and Polymer Concretes.
- ASTM D1308 Standard Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes.
- Crossfield Products Corp. Proprietary Testing.

Note: Chemical resistance is a functional test, usually limited to changes in weight or thickness measured in loss or gain and does not evaluate subject aesthetic issues. To determine aesthetic issues, Crossfield recommends testing the products or system in accordance with intended end use.

9. TESTING

The technical data contained herein is the result of tests made in Crossfield's laboratories or in independent laboratories using small scale equipment, following generally accepted trade practices. Although this information is believed to be true and accurate, the use of different equipment for testing under dissimilar conditions or the testing of samples produced under dissimilar conditions may develop substantially different results.

LIMITED WARRANTY

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICE ARE MET.

Crossfield Products Corp. warrants to the purchaser of its products that such products are free from manufacturing defect. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield's obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and which Crossfield examination shall disclose to Crossfield's satisfaction to be thus defective.

IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION, ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIALS NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCT OR PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.

CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.



DEX-O-TEX PRODUCT LINE Crossfield Products Corp.

West Coast Office
3000 E. Harcourt Street
Rancho Dominguez, CA
90221
310-886-9100
310-886-9119 fax

East Coast Office
140 Valley Road
Roselle Park, NJ
07204
908-245-2800
908-245-0659 fax

www.dexotex.com