

Congratulations on selecting Dex-O-Tex Resistite Protective Cementitious Coating. Just follow the recommendations below to maximize the life of your new surface.

### Cleaning

Cleaning your new Dex-O-Tex Resistite surface is simple. Just wash with a mild cleaning solution such as “Simple Green” or “Ivory Liquid”. Use a brush to remove tough, ground-in soil, stubborn stains or residual compounds. Rinse thoroughly with clean water.

Regular cleaning will prevent build-up of residue, which can make the deck surface slippery when wet. In exterior locations, keep Resistite surfaces swept free of leaves. Decomposing leaves will stain the finish.

### Maintenance

Dex-O-Tex Resistite can be damaged by gouging or scraping with sharp objects and should be protected against such damage. All snow removal should be accomplished using snow shovels which must be carefully handled to avoid damaging the surface. Do NOT use ice chippers on Resistite. The use of chloride-type ice and snow melting compounds will not damage Resistite, although they may leave a white deposit which will require careful cleaning to remove.

Resistite is typically coated with Dex-O-Tex AJ-44 Dressing. The traffic topping is designed to withstand normal everyday wear and direct exposure to the elements when installed as per manufacturers application instructions. Over a period of time the traffic topping needs to be resealed with Dex-O-Tex AJ-44 Sealer Dressing. This is required when traffic patterns become visible in the decking. This should be approximately 5 to 7 years in normal traffic areas and every 3 to 5 years in high traffic areas such as stairways and access corridors.

Should your Dex-O-Tex Resistite installation be damaged, it can be repaired by yourself or a Factory Trained Resistite Applicator. Repair kits (“mini kits”) are available from your Resistite contractor. Each kit contains instructions for use.

### Common Problems to Avoid

Do not lay rubber mats or exterior carpet-type surfacing over Resistite. In order to function properly, Resistite must “breathe”. Prolonged coverage with impermeable matting may result in “bubbling” of the Resistite surface.

Avoid heavy point loads being applied directly to the deck.

Do not expose the deck covering system to harsh chemicals or acids.

Do not subject the deck covering to continuous heavy rolling loads.



### DEX-O-TEX PRODUCT LINE Crossfield Products Corp.

West Coast Office  
3000 E. Harcourt Street  
Rancho Dominguez, CA  
90221  
310-886-9100  
310-886-9119 fax

East Coast Office  
140 Valley Road  
Roselle Park, NJ  
07204  
908-245-2800  
908-245-0659 fax

[www.dexotex.com](http://www.dexotex.com)