

DEX-O-TEX

Product Description Sheet



Advanced Floor
and Waterproof
Systems since
1938

www.dexotex.com

12/20

Crossfield
Products Corp.

California
3000 E. Harcourt St.
Rancho Dominguez,
90221
(310) 886-9100

Texas
128 Industrial Dr.
Cibolo, 78108
(210)888-0449

New Jersey
140 Valley Rd.
Roselle Park, 07204
(908) 245-2800

ME Flooring

Waterproofing Mechanical Equipment Room Floor System
Typical Thickness 1/8" - 3/16"

DESCRIPTION

ME Flooring is a multi-layered troweled flooring system designed for use as a waterproof flooring system for mechanical equipment rooms above occupied areas.

WHERE TO USE

As combination waterproofing and floor finish for mechanical equipment rooms, air conditioning rooms, plenums and similar spaces subject to leakage through inadvertent water spillage.

ADVANTAGES

- Forms a monolithic, tightly adhering, molded waterproof system across floors and up bases, curbs, equipment pads and up pipe sleeves
- Environmentally Friendly, Low Odor During Installation and Cure.
- Slip Resistant
- Easily Maintained
- LEED Credit points may be available
- CDPH 1350 Approval
- Anti-Microbial properties to fight bacteria, fungi, mold and mildew growth

FINISH OPTIONS

- See AJ-44 XL Color Chart, [click here](#), or available at www.dexotex.com
- Optional Dex-O-Tex Posi-Tred Chemical Resistant Topcoats

PHYSICALS	METHOD	RESULTS
VOC in g/L	40 CFR 60, Appendix A-7, method 24	
Waterproofness	Smith-Emery Laboratories Test Procedure (Sample 18" diam. Subjected to 50 lbs. per inch water pressure for 60 mins. Test for amount of water forced through in grams.)	
Elongation Dry	ASTM D1117-01	29.0%
Breakload Dry	ASTM D1117-01	106 lbs. per inch
Elongation Wet	ASTM D1117-01	31.0%
Elongation Wet	ASTM D1117-01	67 lbs. per inch
Strip Adhesion		19.2 lbs. per inch
Indentation	Mil-D-3134	<5%
Resistant to Elevated Temperatures	Mil-D-3134	No flow or slip
Flammability	ASTM E 648	Critical Radiant Flux = 1.1 (w/cm ²)
Flammability	ASTM E 662	Maximum Specific Optical Density (non-flaming) = 245
Flammability	ASTM E 662	Maximum Specific Optical Density (flaming) = 199

The above physical properties were measured in accordance with the referenced standards. Results may vary based upon statistical variations on mixing methods and equipment, application methods, environment, and actual site conditions and curing conditions. All sample preparation and testing are conducted in a laboratory environment and actual performance on job site may vary from these values based on actual site conditions.

Installed by Factory Trained Dex-O-Tex Applicators Only

CARE AND MAINTENANCE

See care and maintenance form, [click here](#), or available at www.dexotex.com

CHEMICAL RESISTANCE

See chemical resistance chart, [click here](#), or available at www.dexotex.com

LIMITATIONS

- Floor finish of system subject to damage by abusive damage from sharp, heavy objects.
- ME Flooring is an aesthetically inconsistent system: texture, profile and final appearance is determined by application technique.
- Sloping, smoothing or leveling compounds, crack repair or isolation, or other supplementary items may be required for proper installation at an additional cost. Consult with Crossfield Products Corp. for specific recommendations.
- Moisture vapor emission rates (MVER) in excess of 3.0 lbs./1000 sq. ft./per 24 hour period per ASTM F1869, or an rh in excess of 78% per ASTM F2170 may result in delamination, discoloration or improper curing without proper treatment prior to installation of the flooring system. Consult with Crossfield Products Corp. for specific recommendations.

LIMITED WARRANTY NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP. INVOICE ARE MET. Crossfield Products Corp. warrants to the purchaser of its products that such products are free from manufacturing defect. Crossfield does not warrant or guarantee the workmanship performed by any person or firm installing its products. Crossfield's obligation under this warranty is limited solely to the original purchaser and solely to the remedy of replacement in kind of any product which Crossfield sold which may prove defective in manufacture within one year from date of installation, provided said product was stored correctly and installed within the product's shelf life, by the original purchaser and which Crossfield examination shall disclose to Crossfield's satisfaction to be thus defective. IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION, ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIALS NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCT OR PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES. CAUTION: ALWAYS KEEP OUT OF THE REACH OF CHILDREN.

Crossfield Products Corp.

California
3000 E. Harcourt St.
Rancho Dominguez,
90221
(310) 886-9100

Texas
128 Industrial Dr.
Cibolo, 78108
(210)888-0449

New Jersey
140 Valley Rd.
Roselle Park, 07204
(908) 245-2800