

DEX-O-TEX

Product Description Sheet



Advanced Floor
and Waterproof
Systems since
1938

www.dexotex.com

2/21

Crossfield Products Corp.

California
3000 E. Harcourt St.
Rancho Dominguez,
90221
(310) 886-9100

Texas
128 Industrial Dr.
Cibolo, 78108
(210) 888-0449

New Jersey
140 Valley Rd.
Roselle Park, 07204
(908) 245-2800

Posi-Tred SL

Pigmented Epoxy Coating
Typical Thickness 7-40 mils

DESCRIPTION

Dex-O-Tex Posi-Tred SL is a high solids two component pigmented epoxy body coat.

WHERE TO USE

Used in wet or dry environments for commercial, industrial, and institutional facilities. Such as food service preparation areas, beverage service areas, entry foyers, labs, pharmaceutical production, and over most Dex-O-Tex Flooring systems.

ADVANTAGES

- High Build
- Can be applied over a wide range of surfaces
- Low odor during installation
- Chemical resistant
- High Gloss finish
- Antimicrobial additive available

FINISH OPTIONS

See Standard Epoxy Color Chart available at www.dexotex.com
Available in 413 Speedway Gray, 431 Bright Gray, and 304 Sandpiper Beiger

PHYSICALS	METHOD	RESULTS
VOC in g/L	40 CRF 60 appendix A7 Method 24	60 g / L
Adhesion	ASTM D 4541	>400 psi
Hardness	ASTM D2240 Shore A	75-80
Taber Abrasion	ASTM D 4060	104 mg loss
Microbial Resistance (with additive)	ASTM G21	Passes Rating 1
Chemical Resistance	See chemical resistance chart	

The above physical properties were measured in accordance with the referenced standards. Results may vary based upon statistical variations on mixing methods and equipment, application methods, environment, and actual site conditions and curing conditions. All sample preparation and testing are conducted in a laboratory environment and actual performance on job site may vary from these values based on actual site conditions.

Installed by Factory Trained Dex-O-Tex Applicators Only

CARE AND MAINTENANCE

See care and maintenance form available at www.dexotex.com

CHEMICAL RESISTANCE

See chemical resistance chart available at www.dexotex.com

LIMITATIONS

- If sub-surface cracks move due to continued thermal flexing or mechanical loads or building settlement, Dex-O-Tex Posi-Tred SL may reflect those cracks to some degree.
- Dex-O-Tex SC Membrane may be used as a waterproofing and crack isolation membrane prior to system application.
- Discoloration may occur under UV exposure, use Dex-O-Tex Quik Glaze when UV stability is required.
- Moisture vapor emission rates (MVER) in excess of 10 lbs./1000 sq/ft/per 24 hr. period per ASTM F1869, or an RH in excess of 85% per ASTM F2170 requires the application of Vapor Control 1P Primer.
- Vapor control primers, sloping, smoothing or leveling compounds, crack repair or isolation, waterproof membranes or other supplementary items may be required for proper installation at an additional cost. Consult with Crossfield Products Corp. for specific recommendations.

NOTE

Crossfield Products Corp. assumes no responsibility or liability for any errors or omissions in the content of this document. The information contained is subject to change without notice.

WARRANTY

All sales are subject to the Crossfield Terms and Conditions effective on the date the purchase order is received. The Terms and Conditions are incorporated herein in full by this reference. The Terms and Conditions are set forth at (www.dexotex.com) and will also be sent by mail or fax to the purchaser upon request. By placing an order, the Buyer acknowledges that it has read and agrees to the provisions of the Terms and Conditions.

Crossfield Products Corp. assumes no responsibility or liability for any errors or omissions in the content of this document. The information contained is subject to change without notice.

Crossfield Products Corp.

California
3000 E. Harcourt St.
Rancho Dominguez,
90221
(310) 886-9100

Texas
128 Industrial Dr.
Cibolo, 78108
(210) 888-0449

New Jersey
140 Valley Rd.
Roselle Park, 07204
(908) 245-2800